



Standard Test Method for Effect of Deflection on Sprayed Fire-Resistive Material Applied to Structural Members¹

This standard is issued under the fixed designation E759; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers a procedure for determining the effect of deflection on sprayed fire-resistive material (SFRM) applied to steel deck. These materials include sprayed fibrous and cementitious materials applied directly in contact with the structural members. The test method is applicable only to laboratory procedures.

1.2 The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E84 Test Method for Surface Burning Characteristics of Building Materials

E119 Test Methods for Fire Tests of Building Construction and Materials

E605 Test Methods for Thickness and Density of Sprayed Fire-Resistive Material (SFRM) Applied to Structural Members

3. Summary of Test Method

3.1 In this test method, a cellular steel deck panel sprayed with fire-resistive material is subjected to bending by a vertical center load while supported horizontally at its ends.

¹ This test method is under the jurisdiction of ASTM Committee E06 on Performance of Buildings and is the direct responsibility of Subcommittee E06.21 on Serviceability.

Current edition approved April 1, 2011. Published May 2011. Originally approved in 1980. Last previous edition approved in 2005 as E759 – 92 (2005). DOI: 10.1520/E0759-92R11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance and Use

4.1 The intent of this test method is to determine properties of direct-applied SFRM that may be used to provide an indication of serviceability. Satisfactory performance of fire-resistive material applied to structural members and assemblies depends upon its ability while in place to withstand the various influences that may occur during the life of the structure, as well as upon its satisfactory performance under fire tests.

4.2 This test method measures the behavior of SFRM when subjected to deflection and evaluates such phenomena as spalling and delamination under bending stress. It is an indication of the ability of SFRM to remain in place and resist removal during anticipated service conditions.

5. Apparatus

5.1 *Supports*—Rigid base to provide at least 50 mm (2 in.) bearing and a clear span between supports of 3 m (10 ft).

5.2 *Bearing Block*—Approximately 50 mm (2 in.) wide, minimum 600 mm (24 in.) long bearing surface designed to distribute the load across the width of the specimen.

5.3 *Load*—Any form of weights or testing machine capable of applying a load normal to the test surface and of developing a deflection of $1/120$ of the clear span of the specimen.

5.4 *Deflection Gage*—A dial or digital micrometer graduated to 0.01 mm (0.001 in.).

6. Materials and Manufacture

6.1 The specimen shall consist of cellular steel deck nominal 40 mm (1½ in.) deep, 600 mm (24 in.) wide, by 3600 mm (12 ft) long, consisting of a 1.5 mm (0.060 in. (18 ga.)) thick galvanized steel fluted top section and a 1.2-mm (0.048-in.) galvanized steel flat bottom section welded together to form four cells 150 mm (6 in.) on center.

6.2 This test method requires the application of SFRM in accordance with manufacturers' published instructions. The apparatus, materials, and procedures used to apply the SFRM for this test shall be representative of application in the field.

6.3 The density of the prepared sample shall be similar to the density tested and reported during the Test Methods **E84** and **E119** fire exposures or as required by the sponsor of the test.

6.4 Determine the density and thickness of each of the laboratory-prepared specimens. Report in accordance with Test Methods **E605**.

7. Test Specimen

7.1 Apply the SFRM to the underside of the steel deck at a minimum 19 mm ($\frac{3}{4}$ in.) thickness. Do not apply the SFRM to the area 330 mm (13 in.) from each end of the specimen, in order to permit the steel deck to bear directly on the supports.

7.2 Condition the prepared specimen for a period of not less than one week at ambient temperature and humidity conditions (but not less than 4.4°C (40°F)) until cured.

7.3 Condition the specimen for a period sufficient to be considered dry in accordance with the manufacturers' recommendation.

8. Procedure

8.1 Place the specimen on the test supports with the SFRM as the lower surface.

8.2 To measure the deflection of the specimen, record the initial reading of the dial micrometer prior to the application of the load and record the deformation as the load is applied.

8.3 Apply a vertical center load to the upper face of the specimen by means of a bearing block to develop a deflection of $\frac{1}{120}$ of the clear span, that is, 25 mm (1.0 in.).

9. Report

9.1 Report the following information:

9.1.1 Condition of the test specimen when it has deflected the required $\frac{1}{120}$ the clear span,

9.1.2 Any spalling or delamination, and

9.1.3 Thickness of the SFRM in millimetres (or inches) and the density in kilograms per cubic metre (or pounds per cubic foot).

10. Precision and Bias

10.1 No statement is made about either precision or bias of this test method since the results merely describe qualitatively the physical condition of the test specimen after exposure to the specified procedure.

11. Keywords

11.1 deflection; sprayed cementitious; sprayed-fire-resistive materials (SFRM)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).